

QUALITY SUMMARY OF 2001 U.S. UPLAND COTTON

CLASSING OFFICE	PERCENT OF BALES									
	WHITEGRADES				LIGHT SPOTTED GRADES				OTHER GRADES	BARKY GRADES
	MID+	SLM	LM-	TOT	MID+	SLM	LM-	TOT		
Florence, SC	78.2	18.9	1.3	98.4	0.6	0.6	0.2	1.4	0.2	0.8
Macon, GA	65.9	26.5	5.6	98.0	0.8	1.0	0.2	2.0	0.0	1.4
Birmingham, AL	67.2	25.0	4.0	96.2	1.5	1.4	0.3	3.2	0.6	3.9
Rayville, LA	17.7	45.6	3.9	67.2	2.9	19.9	5.7	28.5	4.3	0.7
Memphis, TN	45.4	33.5	4.8	83.7	4.9	8.6	1.5	15.0	1.3	0.4
Dumas, AR	33.4	34.0	1.3	68.7	5.5	20.4	2.4	28.3	3.0	0.8
C. Christi, TX	69.7	4.8	0.5	75.0	10.3	1.1	2.6	14.0	11.0	2.1
Abilene, TX	44.3	14.4	1.7	60.4	9.7	14.9	7.1	31.7	7.9	11.2
Lubbock, TX	74.5	2.8	0.0	77.3	16.2	3.1	0.1	19.4	3.3	6.3
Lamesa, TX	77.1	2.8	0.0	79.9	16.3	1.6	0.0	17.9	2.2	3.9
Phoenix, AZ	90.6	4.0	0.2	94.8	4.0	0.8	0.1	4.9	0.3	3.6
Visalia, CA	92.5	2.7	0.6	95.8	2.7	0.6	0.1	3.4	0.8	0.3
AVERAGE	60.6	21.0	2.3	83.9	5.5	6.8	1.4	13.7	2.3	

	MIC unit	LEN 32/in	L.UI (%)	STR g/t	TRASH (%)	MAT RATIO	FIN mtex	LGRD INDEX	NO. BALES	LEN inch
Florence, SC	4.5	34.4	81.5	27.9	0.46	0.937	175	3.4	2,221,875	1.08
Macon, GA	4.4	34.1	81.0	27.9	0.37	0.953	171	3.1	2,191,412	1.07
Birmingham, AL	4.4	34.4	81.3	27.3	0.41	0.935	175	3.2	1,014,336	1.08
Rayville, LA	4.9	34.2	81.1	27.3	0.43	0.991	184	3.3	1,126,293	1.07
Memphis, TN	4.7	34.6	81.9	28.2	0.39	0.969	186	3.2	3,033,523	1.08
Dumas, AR	4.8	34.4	81.6	27.3	0.44	0.985	185	3.3	2,635,648	1.08
C. Christi, TX	4.4	34.4	81.2	28.8	0.34	0.984	165	2.7	956,135	1.08
Abilene, TX	4.6	34.0	80.7	28.2	0.35	0.993	176	3.0	826,639	1.06
Lubbock, TX	4.4	33.6	81.1	28.5	0.25	0.955	175	2.5	2,232,590	1.05
Lamesa, TX	4.5	33.7	80.9	28.5	0.24	0.968	173	2.5	318,315	1.05
Phoenix, AZ	4.6	35.4	80.6	28.0	0.22	1.010	177	2.1	868,666	1.11
Visalia, CA	4.3	36.2	81.6	31.9	0.22	0.997	157	2.4	1,613,643	1.13
AVERAGE	4.56	34.5	81.3	28.3	0.36	0.971	177	3.0	19,039,075	1.08

Classing Week Ending – FINAL 2001

FIBER QUALITY RESEARCH

*Number of physical bales, not calculated by weight. 16.3 million physical bales ~ 16.8 million 480-lb bales.