

QUALITY SUMMARY OF 2005 U.S. UPLAND COTTON - BY CLASSING OFFICE

CLASSING OFFICE	PERCENT OF BALES										MIC unit	LEN 32/in	L.UI (%)	STR g/t	TRASH (%)	LGRD INDEX	NO. BALES	LEN inch
	WHITE GRADES				LIGHT SPOT GRADES				OTHER Grades	BARKY Grades								
	MID+	SLM	LM-	TOT	MID+	SLM	LM-	TOT										
Florence, SC	10.1	43.4	21.1	74.6	0.8	8.6	14.3	23.7	1.7	1.3	4.5	35.0	81.4	28.4	0.56	3.7	1,956,656	1.09
Macon, GA	44.7	49.1	3.6	97.4	0.4	1.3	0.6	2.3	0.3	0.9	4.5	34.7	80.2	29.2	0.41	3.4	2,146,078	1.08
Birmingham, AL	66.9	28.0	1.2	96.1	2.0	1.5	0.1	3.6	0.3	1.9	4.4	34.5	80.8	29.0	0.45	3.5	899,599	1.08
Rayville, LA	76.4	17.6	0.2	94.2	2.9	2.3	0.1	5.3	0.5	0.0	4.7	34.4	80.2	28.6	0.35	3.1	1,185,342	1.08
Memphis, TN	61.6	27.0	0.1	88.7	5.7	5.2	0.1	11.0	0.3	0.5	4.5	34.7	81.5	29.2	0.46	3.5	3,494,442	1.08
Dumas, AR	60.6	24.0	0.2	84.8	6.3	8.5	0.2	15.0	0.2	0.3	4.6	34.7	80.8	28.9	0.48	3.5	2,562,350	1.08
C. Christi, TX	62.2	23.1	2.8	88.1	6.3	4.3	0.7	11.3	0.6	5.3	4.2	34.7	80.8	30.2	0.46	3.6	1,076,190	1.08
Abilene, TX	87.4	2.5	0.1	90.0	7.7	0.4	0.0	8.1	1.9	13.4	4.0	34.3	80.1	28.8	0.28	2.8	2,075,408	1.07
Lubbock, TX	95.1	0.3	0.0	95.4	3.7	0.1	0.0	3.8	0.8	6.7	3.7	34.7	80.2	28.8	0.26	2.8	4,078,557	1.08
Lamesa, TX	96.1	0.8	0.0	96.9	2.5	0.0	0.0	2.5	0.6	12.3	3.8	34.9	80.1	28.7	0.25	2.7	1,472,260	1.09
Phoenix, AZ	90.1	5.5	0.2	95.8	3.3	0.5	0.0	3.8	0.4	4.2	4.5	35.5	80.5	29.3	0.19	2.3	726,100	1.11
Visalia, CA	95.8	1.5	0.0	97.3	1.8	0.4	0.0	2.2	0.5	0.6	4.3	37.4	82.5	34.1	0.23	2.7	965,265	1.17
AVERAGE	69.5	19.0	2.4	90.9	3.9	3.1	1.4	8.4	0.7		4.26	34.8	80.7	29.2	0.38	3.2	22,638,247	1.09

Classing Week Ending - FINAL 2005

FIBER QUALITY RESEARCH

Comparison to last year's crop at this time

U.S. Average	FINAL 2004	FINAL 2005
Total White Grade	84.2 %	90.9 %
Total Light Spotted Grade	12.2 %	8.4 %
Average Micronaire	4.27	4.26
Average Length (32's)	34.9 (32/in)	34.8 (32/in)
(Inches)	1.09 (in)	1.09 (in)
Average Strength	29.2 (g/tex)	29.2 (g/tex)
Number of Bales Classed	21,831,905	22,638,247

