

QUALITY SUMMARY OF 2010 U.S. UPLAND COTTON - BY CLASSING OFFICE

CLASSING OFFICE	PERCENT OF BALES											STR g/t	TRASH (%)	LGRD INDEX	NO. BALES	LEN inch		
	WHITE GRADES				LIGHT SPOT GRADES				OTHER BARKY Grades	MIC unit	LEN 32/in						L.UI (%)	
	MID+	SLM	LM-	TOT	MID+	SLM	LM-	TOT										
Florence,SC	16.7	32.7	20.1	69.6	1.8	11.4	16.1	29.4	1.0	0.3	4.83	34.9	81.39	28.98	0.42	3.4	1,401,949	1.088
Macon,GA	49.9	43.0	1.7	94.6	2.2	2.7	0.2	5.2	0.2	1.0	4.71	34.9	80.91	29.60	0.39	3.3	2,636,040	1.086
Birmingham,AL	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.00	00.0	00.00	00.00	0.00	0.0		0.000
Rayville,LA	73.1	22.5	1.0	96.6	1.2	2.1	0.1	3.4	0.1	0.5	4.91	35.0	81.06	29.35	0.40	3.5	457,786	1.090
Memphis,TN	79.9	18.4	0.2	98.5	0.8	0.6	0.0	1.5	0.0	0.1	4.83	35.2	81.44	30.39	0.34	3.2	2,432,494	1.098
Dumas,AR	78.7	16.9	0.2	95.8	2.3	1.7	0.1	4.1	0.1	0.3	4.93	35.0	81.35	29.71	0.40	3.5	1,010,868	1.090
C.Christi,TX	56.7	20.5	4.4	81.7	5.1	6.8	3.7	15.6	2.8	4.5	4.65	36.2	82.21	30.80	0.39	3.5	960,065	1.130
Abilene,TX	84.9	4.6	0.3	89.7	6.2	2.6	0.3	9.1	1.2	8.5	4.48	35.0	80.65	29.97	0.25	2.4	1,924,773	1.092
Lubbock,TX	96.3	0.1	0.0	96.5	2.8	0.0	0.0	2.8	0.7	9.1	4.03	36.0	80.59	30.19	0.22	2.3	3,943,280	1.121
Lamesa,TX	95.0	0.3	0.0	95.3	3.6	0.1	0.0	3.7	1.0	9.0	4.34	35.4	80.65	29.52	0.20	2.1	1,344,646	1.101
Phoenix,AZ	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.00	00.0	00.00	00.00	0.00	0.0		0.000
Visalia,CA	89.2	5.9	0.3	95.4	2.5	1.2	0.3	4.0	0.7	2.9	4.32	37.1	81.50	31.24	0.23	2.4	1,024,952	1.156
AVERAGE	74.6	15.6	2.3	92.5	2.8	2.4	1.6	6.8	0.7	4.4	4.52	35.5	81.04	30.00	0.31	2.8	17,136,853	1.105

Final 2010

FIBER COMPETITION



<u>U.S. Average</u>	<u>Final 2009</u>	<u>Final 2010</u>
Total White Grade	92.7 %	92.5 %
Total Light Spotted Grade	06.2 %	06.8 %
Average Micronaire	4.18	4.52
Average Length (32's)	35.5 (32/in)	35.5 (32/in)
(Inches)	1.105 (in)	1.105 (in)
Average Strength	29.08 (g/tex)	30.00 (g/tex)
Number of Bales Classed	11,415,668	17,136,853

Summary by Fiber Competition, Cotton Incorporated
 Data furnished by USDA- Cotton Market News

QUALITY SUMMARY OF 2010 U.S. UPLAND COTTON - BY CLASSING OFFICE

CLASSING OFFICE	PERCENT OF BALES														NO. BALES	LEN inch		
	WHITE GRADES				LIGHT SPOT GRADES				OTHER BARKY Grades	MIC unit	LEN 32/in	L.UI (%)	STR g/t	TRASH (%)			LGRD INDEX	
	MID+	SLM	LM-	TOT	MID+	SLM	LM-	TOT										
Florence,SC	16.7	32.7	20.1	69.6	1.8	11.4	16.1	29.4	1.0	0.3	4.83	34.9	81.39	28.98	0.42	3.4	1,401,949	1.088
Macon,GA	49.9	43.0	1.7	94.6	2.2	2.7	0.2	5.2	0.2	1.0	4.71	34.9	80.91	29.60	0.39	3.3	2,636,040	1.086
Birmingham,AL	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.00	00.0	00.00	00.00	0.00	0.0		0.000
Rayville,LA	73.1	22.5	1.0	96.6	1.2	2.1	0.1	3.4	0.1	0.5	4.91	35.0	81.06	29.35	0.40	3.5	457,786	1.090
Memphis,TN	79.9	18.4	0.2	98.5	0.8	0.6	0.0	1.5	0.0	0.1	4.83	35.2	81.44	30.39	0.34	3.2	2,432,494	1.098
Dumas,AR	78.7	16.9	0.2	95.8	2.3	1.7	0.1	4.1	0.1	0.3	4.93	35.0	81.35	29.71	0.40	3.5	1,010,868	1.090
C.Christi,TX	56.7	20.5	4.4	81.7	5.1	6.8	3.7	15.6	2.8	4.5	4.65	36.2	82.21	30.80	0.39	3.5	960,065	1.130
Abilene,TX	84.9	4.6	0.3	89.7	6.2	2.6	0.3	9.1	1.2	8.5	4.48	35.0	80.65	29.97	0.25	2.4	1,924,773	1.092
Lubbock,TX	96.3	0.1	0.0	96.5	2.8	0.0	0.0	2.8	0.7	9.1	4.03	36.0	80.59	30.19	0.22	2.3	3,943,280	1.121
Lamesa,TX	95.0	0.3	0.0	95.3	3.6	0.1	0.0	3.7	1.0	9.0	4.34	35.4	80.65	29.52	0.20	2.1	1,344,646	1.101
Phoenix,AZ	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.00	00.0	00.00	00.00	0.00	0.0		0.000
Visalia,CA	89.2	5.9	0.3	95.4	2.5	1.2	0.3	4.0	0.7	2.9	4.32	37.1	81.50	31.24	0.23	2.4	1,024,952	1.156
AVERAGE	74.6	15.6	2.3	92.5	2.8	2.4	1.6	6.8	0.7	4.4	4.52	35.5	81.04	30.00	0.31	2.8	17,136,853	1.105

Final 2010

FIBER COMPETITION



<u>U.S. Average</u>	<u>Final 2009</u>	<u>Final 2010</u>
Total White Grade	92.7 %	92.5 %
Total Light Spotted Grade	06.2 %	06.8 %
Average Micronaire	4.18	4.52
Average Length (32's)	35.5 (32/in)	35.5 (32/in)
(Inches)	1.105 (in)	1.105 (in)
Average Strength	29.08 (g/tex)	30.00 (g/tex)
Number of Bales Classed	11,415,668	17,136,853

Summary by Fiber Competition, Cotton Incorporated
 Data furnished by USDA- Cotton Market News